

MAGNETIC BLACKBOARD

PRODUCT

Quick drying ferromagnetic spray-paint.

PROPERTIES AND FIELDS OF USE

Special paint with additional pigments that attract magnets. All objects with magnets can be applied to the treated surface. Apply more coats to get more power of attraction. Excellent hardness and good adhesion on various types of materials. High covering power. It can be used as a blackboard by writing with chalk. For cleaning you can use a cloth soaked in water.

Ideal for: INDUSTRY - CRAFTS - DIY.

SURFACES

High adhesion on numerous supports such as metal (iron, brass, steel), ABS plastics (no PP or similar), wood, glass, stone, cement. For plastic surfaces, apply the plastic anchoring base beforehand. Use preferably on smooth surfaces. Incompatibility: do not apply on surfaces with residues of products containing silicones. Do not apply on polystyrene. Application on synthetic paints is not recommended.

TECHNICAL SPECIFICATIONS

Binder	Modified acrylic
Yield	1 m ²
Pressure at 20 °C	from 4.2 to 4,8 bar
Pressure at 50 °C	from 7.6 to 8.4 bar
COV	see SDS Sec. 9.1 and 15.3
Gloss level:	matt
Drying time:	
Dust-free	5-8 minutes
Dry to touch	15-20 minutes
Deep dry	16-20 hours

INSTRUCTIONS FOR USE

Before use carefully read the instructions on the can and consult the SDS for safe handling of the product (Sec. 7.1).

Use between 10 and 25 °C on surfaces at the same temperature, in well ventilated environments. Mask the parts not to be treated. Remove residues of rust or paint not anchored. Degrease. Shake the can vigorously for approx. 2 minutes from the moment you feel the mixing balls. Preferably apply on a perfectly smooth surface. To level the surfaces use the filler base in advance. Make a spray test on a separate surface. Spray a layer cross-over, from a distance of 20-25 cm. To obtain a greater effect of attraction of the magnets, repeat the application with several coats interspersed every about 15 minutes.



Sede Legale, Amministrativa e Operativa: Via Benvenuto Cellini 26, 20033 Solaro (Mi)

C.C.I.A.A. Milano 1172121

Codice fiscale e Partita IVA: 01485370124

Capitale sociale: Euro 1.000.000,00 interamente versato

Contacts: Phone: +39 02 9690664 Fax: +39 02 9691714

Website: www.colorpack.com Email: info@colorpack.com

SDI CODE: BY5KTZZ

On plastics we recommend the use of the special primer. Every time you finish the application, turn the can upside down and spray for a few seconds until the product comes out so you can clean the spray-head.

For further information refer to the SDS: labelling (Sec. 2.2), storage (Sec. 7.2) and disposal (Sec. 13).

EXEMPTION FROM LIABILITY

The information contained in this document is provided to the best of our scientific knowledge. However, they should be regarded as non-binding indications and do not release the consumer from personally carrying out checks on the products as to their compatibility with their intended uses. Colorpack Srl is relieved of any liability if any damage is not link to specific causes attributable to the same Colorpack Srl.

THE LABORATORY/QMS



Sede Legale, Amministrativa e Operativa: Via Benvenuto Cellini 26, 20033 Solaro (Mi)

C.C.I.A.A. Milano 1172121

Codice fiscale e Partita IVA: 01485370124

Capitale sociale: Euro 1.000.000,00 interamente versato

Contacts: Phone: +39 02 9690664 Fax: +39 02 9691714

Website: www.colorpack.com Email: info@colorpack.com

SDI CODE: **BY5KTZZ**